



MC-DUR 1209 TX

Thixotropic adhesive for CF-sheets for structural reinforcement

Product Properties

- Two-component adhesive based on epoxy resin
- High mechanical strength
- Application even at high temperatures (≤ 40 °C)
- Excellent adhesive between CF-sheets and prepared substrate
- High structural stability

Areas of Application

- Adhesive for high-tensile reinforcing sheets for reinforcement of components made of reinforced concrete and brickwork
- REACh-assessed exposure scenarios: periodical water-contact, periodical inhalation, application

Application

Substrate Preparation

Before application of MC-DUR 1209 TX all substrates must be verified for load-bearing capacity and prepared by means of a suitable surface blasting method. The substrates must be dry (residual moisture ≤ 6 %, CM-method), free of cement laitance, dust, oil and other contaminants. A minimum pull-off strength of 1.5 N/mm^2 is required. The bonding surfaces of the substrate must be protected from increasing backwards moisture.

Before application of CF-sheets the evenness of the concrete surface must be checked. The levelling mortar MC-DUR 1000 Parat 09 can be used for levelling (roughness $< 1.5 \text{ mm}$) according to the application advice indicated in the technical data sheet.

Mixing and Application

MC-DUR 1209 TX consists of two components, supplied in prepacked quantities. First, the base component is mixed thoroughly and then the hardener is added. Both components are mixed together thoroughly and homogeneously for at least 3 minutes. Slowly rotating mixers with paddle (max. 300 rpm) are suitable for mixing. Care should be taken to keep entrainment of air to a minimum while mixing.

After mixing the resin must be refilled into a clean container and mixed again.

MC-DUR 1209 TX is applied at least 0.5 mm thick onto the substrate, using a trowel, a scraper or similar tool. Afterwards the CF-sheets are pressed into the fresh adhesive, using a laminating roller or similar tool, and then coated with MC-DUR 1209, applied with a roller. Care must be taken during application that the carbon fibres are completely embedded in the adhesive.

General Information

High temperatures shorten while low temperatures extend all indicated times and intervals. As a rule of thumb a change in temperature of 10 °C either halves or doubles the indicated pot life.

Furthermore please note that higher temperatures reduce both the viscosity and the thixotropic properties of MC-DUR 1209 TX.

Varnish runs must be avoided. MC-DUR 1209 TX should be stored inside at cool temperatures.

Safety Advice

Please take notice of the safety information and advice given on the packaging labels and safety data sheets.



Technical Data for MC-DUR 1209 TX

Characteristic	Unit	Value*	Comments
Mixing ratio	p. b. w.	3 : 1	base : hardener
Density	kg/dm ³	1.33	
Viscosity	mPa·s	-	thixotrope
Coverage	kg/m ² and mm	1.33	
Layer thickness / strength	mm	10	
Pot Life at 20 °C	minutes	50 40	12 kg 30 kg
Application conditions	°C	≥ 8; ≤ 40** ≥ 15; ≤ 25	air and substrate temperature material temperature
	%	≤ 85	relative humidity
	K	3	above dew point
E-Modulus	MPa	approx. 4,700	at 20 °C and 50 % relative humidity
Adhesive tensile strength	MPa	14	steel/steel (die Ø 20 mm)

Product Characteristics for MC-DUR 1209 TX

Cleaning agent	MC-Reinigungsmittel U (MC-cleaning agent U)
Colour	grey
Delivery	12 kg and 30 kg packs
Storage	Can be stored in original sealed packages at temperatures below 20 °C (recommended > 15 °C - < 20 °C) in dry conditions for at least 12 months. Protect from frost! The same requirements are valid for transport.
Disposal	Packs must be emptied completely.

* All technical data relate to 20 °C and 50 % relative humidity.

** At substrate temperatures > 30 °C the different layers of MC-DUR CF-Sheets must be applied fresh in fresh.

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 02/12. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.