

ombran W

Fast-setting, expanding plugging mortar to stop water intrusions.

Product properties

- Rapidly seals water intrusions
- Expands during the curing process when exposed to water (swelling effect)
- Does not contain any substances that promote corrosion
- Soundness in accordance with DIN 1164

Areas of application

- Rapid stopping of leaks and water intrusions in structures of concrete, masonry and natural stone
- Sealing pipe penetrations and pipe connections
- Retro-sealing of damaged pipe couplings and manhole ring joints
- Sealing of internal corners of components and transitions between components

Application

Preparation of the substrate

See the data sheet "General instructions for shaft and sewer rehabilitation mortars". Damaged areas must be cut back at 45° (at least 3 cm deep to improve adhesion to the substrate).

Mixing

The fast-setting sealing mortar is prepared using ombran W ready-mix mortar and water. Small amounts to suit the defective site must be mixed by hand for 15 to 20 seconds until a firm plastic uniform mortar is obtained.

Mix ratio

See the "Technical properties" table. About 0.2 litres of water are needed for a 1 kg sack of ombran W. Since ombran W is cement-bound, the amount of water needed may vary.

Processing

At water intrusions, press the stiffish mortar into

the deepest part of the leak and apply pressure for about one to two minutes. Immediately after this, any excess material can usually be removed with a trowel or similar. When doing this, always work outwards from the middle, otherwise there is a risk of the not yet fully cured mortar becoming detached from the substrate.

Safety instructions

Observe the hazard notices and safety advice on the labels and safety data sheets.

Other instructions

Ombran W is a rigid, mineral material. Subsequent cracks, settling and deformation due to construction work may result in further leaks. To prevent moisture emerging in the area of the repaired damage, it is a good idea to work over those surfaces with ombran ASP mineral sealing slurries.



Technical Data for ombran W

Characteristic	Unit	Value	Comments
Mix ratio	Parts(by mass)	100 : 20	ombran W: water
Processing time:	minutes	about 1	
Temperature of use	°C	+5 to +30	Air and substrate temperature
Consumption**	kg/m ² /mm	about 1.7	Dry mortar
Fresh mortar raw density	kg/l	about 2.0	
Development of compressive strength	N/mm ²	about 8.0 about 10.0 about 13.0 about 25.0 about 40.0 about 40.0	after 1 h after 3 h after 6 h after 1 d after 7 d after 28 d
Development of bending tensile strength	N/mm ²	about 3.0 about 3.5 about 4.0 about 7.5 about 5.5 about 5.0	after 1 h after 3 h after 6 h after 1 d after 7 d after 28 d

Product Characteristics for ombran W

Colour	Grey
Form of delivery	15 kg tub
Equipment cleaner	water
Storage	If tightly sealed, the original packs can be stored for at least one year at temperatures between +5 °C and +25 °C in dry conditions. The same requirements apply to transport.
Pack disposal	Make sure the pack is completely empty. Refer to our information sheet on the packaging order "The MC disposal concept for completely empty transport and sales packaging". We would be pleased to send you this on request.

* Unless otherwise stated, all technical data were determined at +23 °C und 50 % relative air humidity.

** Quantities used depend on the object and on the roughness of the substrate as well as on the storage and working temperatures and the temperature of the substrate. We recommend carrying out experiments beforehand to determine object-specific quantities.

Note: The information on this data sheet is based on our experiences and correct to the best of our knowledge. It is, however, not binding. It has to be adjusted to the individual structure, application purpose and especially to local conditions. Our data refers to the accepted engineering rules, which have to be observed during application. This provided we are liable for the correctness of this data within the scope of our terms and conditions of sale-delivery-and-service. Recommendations of our employees which differ from the data contained in our information sheets are only binding if given in written form. The accepted engineering rules must be observed at all times.

Edition 01/09. Some technical changes have been made to this print medium. Older editions are invalid and may not be used anymore. If a technically revised new edition is issued, this edition becomes invalid.